

## REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

AD-A268 148



It is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering the necessary data, reviewing the collection of information, sending comments regarding this burden estimate or any other aspect of this collection of information, including this burden estimate, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

2. REPORT DATE  
15 June 933. REPORT TYPE AND DATES COVERED  
Final Report 15 Jan 90 - 14 Jan 93Basic optical studies of High T<sub>c</sub> Oxide superconductors5. FUNDING NUMBERS  
AFOSR-90-0123

## 6. AUTHOR(S)

Professors M.S. Dresselhaus, G. Dresselhaus

## 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Massachusetts Institute of Technology  
Center for Materials Science & Engineering  
77 Massachusetts Avenue  
Cambridge, MA 021398. PERFORMING ORGANIZATION  
REPORT NUMBER

AFOSR-TR. 93 0584

## 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

AFOSR/NE  
110 Duncan Avenue Suite B115  
Bolling AFB, DC 20332-000110. SPONSORING/MONITORING  
AGENCY REPORT NUMBER

2306/C1

## 11. SUPPLEMENTARY NOTES

## 12a. DISTRIBUTION/AVAILABILITY STATEMENT

UNLIMITED

## 12b. DISTRIBUTION CODE

## 13. ABSTRACT (Maximum 200 words)

DTIC  
ELECTE  
AUG 18 1993  
S A D

This document has been approved  
for public release and sale; its  
distribution is unlimited.

SEE REPORT FOR ABSTRACT

## 14. SUBJECT TERMS

## 15. NUMBER OF PAGES

7

## 16. PRICE CODE

17. SECURITY CLASSIFICATION  
OF REPORT

UNCLASSIFIED

18. SECURITY CLASSIFICATION  
OF THIS PAGE

UNCLASSIFIED

19. SECURITY CLASSIFICATION  
OF ABSTRACT

UNCLASSIFIED

## 20. LIMITATION OF ABSTRACT

UL

**Final Technical Report  
to the  
Air Force Office of Scientific Research  
for research on  
BASIC OPTICAL STUDIES OF HIGH  $T_c$   
OXIDE SUPERCONDUCTORS**

AFOSR Agreement #90-0123  
for the period  
January 15, 1990 — January 14, 1993

AFOSR-TR. 93 0584

Principal Investigator: M.S. Dresselhaus  
Co-Principal Investigator: G. Dresselhaus  
Room 13-3005  
Massachusetts Institute of Technology  
Center for Materials Science and Engineering  
77 Massachusetts Avenue  
Cambridge, MA 02139  
Tel. (617) 253-6864

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

DTIC QUALITY INSPECTED 3

June 15, 1993

## Annual Report

### Abstract

During the 1992-93 year of the research program on "Basic Optical Studies of High  $T_c$  Oxide Superconductors", the effort was focused on a number of projects. The collaborative study of the microwave properties of superconductors with researchers at Rome Labs and the MIT Lincoln Laboratory continued and significant results were obtained on the microwave behavior in the non-linear high rf power regime for  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$  and this work will be a major part of the Ph.D. thesis of Paul Nguyen. During this year we continued study of the effect of halogen doping on the restoration of superconductivity to YBCO samples previously deoxygenated, and hence rendered non-superconducting. Extensive progress was also made on our new effort in studying superconductivity and the associated phonon spectra and electron-phonon interaction in the alkali metal doped  $\text{C}_{60}$  materials. We review in this report the progress that was made on each of these projects, referring to the publications that were prepared on each of the topics under investigation.

### Microwave Properties of High $T_c$ Superconductors

A main topic under investigation has been the experimental measurement and theoretical modeling of the microwave properties of high temperature superconductors, carried out as a collaborative effort between researchers at MIT (including an MIT Physics graduate student Paul Nguyen, who is working on his Ph.D. thesis), Rome Labs and the MIT Lincoln Laboratory.

The nonlinearity of the surface resistance  $R_s$  of  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$  as a function of the microwave power level is of great importance for passive microwave devices. Since  $R_s$  depends upon the microwave current  $I_{\text{rf}}$  and microwave magnetic field  $H_{\text{rf}}$ , microwave circuit designs must consider the losses, harmonic generation and intermodulation distortion at the operating power levels. Microwave frequency  $1/f$  noise may also be related to nonlinear conduction processes. The dependence of  $R_s$  on the microwave magnetic field ( $R_s(H_{\text{rf}})$ ) must therefore be measured, since materials with comparable low-field  $R_s$  values can differ substantially in their rf field dependencies. To address this issue, we have carried out the first complete characterization of the nonlinear properties of high-quality  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$  thin films by measuring  $R_s(H_{\text{rf}})$  for  $H_{\text{rf}}$  from 0 to approximately 1 kOe, versus temperature from 4.2K to  $T_c$ , and versus frequency from 1.5 GHz to 20 GHz using a stripline resonator. At all frequencies, there is a sharp increase in the nonlinearity at about 60 K. At low fields, flux penetration at weak links dominates the behavior, while at high fields and temperatures, losses

due to pair breaking or flux flow cause the nonlinearities. In this work we have explored the various mechanisms causing the nonlinearities and how the field dependencies are related to film structure and quality. The results have been interpreted in terms of a coupled-grain model which shows good agreement with the experimentally measured  $R_s(H_H)$ . The imaginary part of  $Z_s(H_H)$ , i.e.,  $X_s(H_H)$ , however, does not seem to fit the model.

Several publications on this topic have been completed during the grant period January 15, 1992 – January 14, 1993 (#1,2,6,9).

### Halogen substitution experiments

The restoration of superconductivity to partially de-oxygenated non-superconducting  $\text{YBa}_2\text{Cu}_3\text{O}_{6.2}$  crystals through halogen substitution (#4) has stimulated a large amount of scientific and technological interest in the compound  $\text{YBa}_2\text{Cu}_3\text{O}_x\text{X}_y$  where X is a halogen. Since bromine addition can be carried out at much lower temperatures ( $\sim 230^\circ\text{C}$ ) than oxygen annealing, the halogenation approach for the restoration of  $T_c$  is of technological interest.

To carry out transport measurements including temperature dependent resistivity and magnetoresistance measurements, we have prepared de-oxygenated non-superconducting  $\text{YBa}_2\text{Cu}_3\text{O}_{6.2}$  single crystals and we have subsequently doped them with Br. The resulting crystals become superconducting with  $T_c \sim 92$  K,  $\Delta T_c \sim 1.0$  K as determined by four-point probe resistivity measurements. The normal state resistivity in our best sample decreases linearly with decreasing temperature. We found a large ratio in the resistivity at 300 K of the brominated to the pristine YBCO single crystals ( $\sim 35:1$ ), suggesting that bromination greatly increases the scattering rate. For these samples we have determined by resistivity measurements the upper critical field  $H_{c2}(T)$  parallel and perpendicular to the  $ab$  plane.  $H_{c2}(0)$  and the corresponding coherence lengths  $\xi_{ab}(0)$  and  $\xi_c(0)$  were then estimated from the Ginzburg-Landau relations. A comparison with the fully oxygenated YBCO single crystals show that  $\xi_{ab}(0)$  remains approximately the same upon bromination, whereas  $\xi_c(0)$  decreases by a factor of  $\sim 3$ , suggesting that Br never enters the  $\text{CuO}_2$  planes. The pinning energy for vortex motion in the  $ab$  plane decreases after bromination and this decrease can be attributed to the increased anisotropy. For vortex motion along the  $\hat{c}$ -axis, however, the pinning energy decreases or increases depending on temperature and field. Compared with the fully oxygenated YBCO single crystals, the critical current density is suppressed by bromination and is strongly dependent on the applied magnetic field. The reduced lower critical field  $H_{c1}$  in the brominated YBCO single crystals indicates a reduction in the carrier density (by a factor of between 2 and 3), which is consistent with the observed reduction in the plasma frequency.

A paper based on this work has been prepared and accepted for publication (#4).

### **Phonons and Electron-Phonon Coupling in $C_{60}$ and Doped $C_{60}$**

The alkali metal doped  $C_{60}$  compounds are particularly interesting because of their relatively high values of  $T_c$ . Because of the importance of the electron-phonon interaction in superconductors, we have initiated a detailed study of phonons and the electron-phonon interaction in alkali metal doped  $C_{60}$ . Our initial work has addressed the phonon spectrum and subsequently the electron-phonon interaction in undoped and doped  $C_{60}$  will be studied.

A force constant model has been developed for the vibrational modes in  $C_{60}$ , based on bond-stretching and angle-bending interactions (#3). The result of this model are compared with the experimental data available from Raman, infrared, and high resolution electron energy loss spectroscopies, as well as neutron inelastic scattering measurements. Excellent agreement is obtained between calculation and experiment. This force constant model not only provides the mode frequencies but also all the eigenvectors. This model for  $C_{60}$  has subsequently been extended to treat  $C_{70}$  and alkali metal doped  $C_{60}$  and  $C_{70}$  (#11,12). These results have been very useful for the interpretation of experimental Raman spectra in  $C_{70}$ ,  $M_xC_{60}$  and  $M_xC_{70}$  films (#17). A model for the phonon spectra of carbon nanotubes has also been developed (#18) utilizing the generalized symmetry properties of carbon nanotubes (#15).

An expression for the electron-phonon coupling strength in fullerene nanotubules has been derived within the tight binding model. It is estimated that under ideal circumstances, the electrical conductivity of metallic fullerene nanotubules could be an order of magnitude larger than that of copper. What is of particular interest is the limited availability of scattering states for such a 1D electron system and the special restrictions for scattering of longitudinal modes (intra-branch scattering only) and transverse modes (inter-branch scattering only). This work has been submitted for publication (#16).

The influence of curvature on the electron-phonon coupling in  $C_{60}$  doped with alkali metals has been studied within the tight-binding formulation. It is shown that the modulation of the tight binding matrix element due to the displacement of atoms from equilibrium has a value which is essentially the same as in graphite. Nevertheless, the existence of coupling between the electrons and the low-frequency radial phonons in  $M_3C_{60}$ ,  $M$  being an alkali-metal atom, leads to a reasonably large value of  $\lambda$ , the dimensionless electron-phonon coupling parameter. The superconducting transition temperature is then readily calculated and is found to be in the experimentally observed range (#8).

Experimental transport studies of weak localization effects in the normal state of superconducting  $K_3C_{60}$  films have been carried out (#10). The femtosecond dynamics of  $K_3C_{60}$  and  $Rb_3C_{60}$  films have been investigated experimentally and related to that observed in  $C_{60}$  films before intercalation, showing a great enhancement in coupling between electrons and phonons in the metallic  $M_3C_{60}$  system relative to that in the precursor insulating  $C_{60}$  film. These results have been related to interband processes in the respective materials. The relation of these findings to the observation of superconductivity in  $M_3C_{60}$  films has also been discussed (#14).

Several review articles relevant to fullerenes were prepared (#5,13).

## **Invited Talks and Honors**

### **Honors**

- Elected Treasurer of the National Academy of Sciences
- Honorary D.Sc., University of Massachusetts, Boston
- Honorary D.Sc., University of Connecticut
- Honorary D.Sc., Princeton University
- Houston Lecturer, Rice University

### **Research Lectures related to work supported by this grant**

- Jan. 16, 1992  
General Motors Research Laboratory
- Jan. 21, 1992  
MIT Club of Boston
- Jan. 28, 1992  
George Washington University and the National Science Foundation
- Feb. 17, 1992  
WPI
- Mar. 3, 1992  
Williams College
- Apr. 30, 1992  
MIT, Math Department Lecture
- May 19, 1992  
Electrochemical Society, Invited talk

- May 21, 1992  
CalTech Physics Colloquium
- May 26, 1992  
AT&T Bell Laboratory
- May 27, 1992  
Princeton University Symposium
- Aug. 3, 1992  
Hokkaido - Hironaka Symposium
- Oct. 1, 1992  
Emery University
- Oct. 14, 1992  
NEC Symposium, Karuizawa, Japan; invited talk
- Oct. 15, 1992  
NEC Symposium, Karuizawa, Japan; Summary talk
- Nov. 29, 1992  
MRS Tutorial on Fullerenes
- Dec. 8, 1992  
University of Maryland
- Jan. 10, 1993  
Houston Lecture, Rice University
- Jan. 12, 1993  
Houston Lecture, Rice University

## **New Discoveries, Patents or Inventions**

None.

## **Publications**

1. C. C. Chin, D. E. Oates, G. Dresselhaus, and M. S. Dresselhaus, Non-linear electrodynamics of superconducting NbN and Nb thin films at microwave frequencies, *Phys. Rev.* **B45**, 4788 (1992).
2. C. C. Chin, D. E. Oates, G. Dresselhaus, and M. S. Dresselhaus. Non-linear microwave electrodynamics of superconducting NbN and Nb thin films, In *Advances in Superconductivity IV*, edited by H. Hayakawa

and N. Koshizuka, page 167, Springer-Verlag, Tokyo, Berlin, New York, 1991. Proceedings of the 4<sup>th</sup> International Symposium on Superconductivity (ISS'91), October 14-17, 1991, Tokyo.

3. R. A. Jishi, R. M. Mirie, and M. S. Dresselhaus, Force constant model for the vibrational modes in  $C_{60}$ , *Phys. Rev.* **B45**, 13685 (1992).
4. P. P. Nguyen, Z. H. Wang, A. M. Rao, M. S. Dresselhaus, J. S. Moodera, G. Dresselhaus, H. B. Radousky, R. S. Glass, and J. Z. Liu, Transport and Magnetic Properties of  $YBa_2Cu_3O_{7-\delta}Br_y$  Single Crystals, *Phys. Rev.* **B46**, xxx (1993). in press, BV4786.
5. M. S. Dresselhaus, G. Dresselhaus, and P. C. Eklund, in *Encyclopedia of Applied Physics*, page 515, edited by Rita G. Lerner and George L. Trigg (AIP, New York, 1993). Fullerenes, Volume 6.
6. D. E. Oates, P. P. Nguyen, G. Dresselhaus, M. S. Dresselhaus, C. W. Lam, and S. M. Ali, Measurements and Modeling of Linear and Non-linear Effects in Striplines, *J. of Superconductivity* **5**, 361 (1992). Conference Proceedings.
7. R. A. Jishi, R. M. Mirie, and M. S. Dresselhaus. A model calculation for the vibrational modes in  $C_{60}$ , In *Novel Forms of Carbon: MRS Symposia Proceedings, San Francisco, volume 270*, edited by C. L. Renschler, J. Pouch, and D. Cox, page 197. Materials Research Society Press, Pittsburgh, PA, 1992.
8. R. A. Jishi and M. S. Dresselhaus. Electron-Phonon Coupling in Superconducting Alkali-Metal Doped Fullerenes, In *Novel Forms of Carbon: MRS Symposia Proceedings, San Francisco, volume 270*, edited by C. L. Renschler, J. Pouch, and D. Cox, page 161. Materials Research Society Press, Pittsburgh, PA, 1992.
9. D. E. Oates, P. P. Nguyen, G. Dresselhaus, M. S. Dresselhaus, and C. C. Chin, Nonlinear Surface Resistance in  $YBa_2Cu_3O_{7-x}$  Thin Films, (1993). Proceedings of the Applied Superconductivity Conference, *IEEE Trans. Appl. Superconductivity* **3**, 1114.
10. Z. H. Wang, A. W. P. Fung, G. Dresselhaus, M. S. Dresselhaus, K. A. Wang, P. Zhou, and P. C. Eklund, Weak localization and electron-electron interactions in  $K_3C_{60}$  films, *Phys. Rev.* **B47** (1993). in press.
11. R. A. Jishi, R. M. Mirie, M. S. Dresselhaus, G. Dresselhaus, and P. C. Eklund, Force constant model for the vibrational modes in  $C_{70}$ , *Phys. Rev.* **BXX** (1993). accepted, 2/17/93: BB5231.



12. R. A. Jishi, M. S. Dresselhaus, G. Dresselhaus, K. A. Wang, Ping Zhou, A. M. Rao, and P. C. Eklund, Vibrational Mode Frequencies in  $C_{70}$ , Chem. Phys. Lett. **206**, 187 (1993).
13. M. S. Dresselhaus, G. Dresselhaus, and P. C. Eklund, Fullerenes, J. Mater. Res. **8** (1993). in press.
14. S. B. Fleischer, E. P. Ippen, G. Dresselhaus, M. S. Dresselhaus, A. M. Rao, P. Zhou, and P. C. Eklund, Femtosecond optical dynamics of  $C_{60}$  and  $M_3C_{60}$ , Appl. Phys. Lett. **25** (1993). in press.
15. R. A. Jishi, M. S. Dresselhaus, and G. Dresselhaus, Symmetry Properties of Chiral Carbon Nanotubes, Phys. Rev. **BXX** (1993). PRB Rapid Comm. accepted 4/9/93: BBS510.
16. R. A. Jishi and M. S. Dresselhaus, Electron-Phonon Coupling and the Electrical Conductivity of Fullerene Nanotubules, Phys. Rev. (1993). submitted 2/22/93: BB5261.
17. K. A. Wang, Ping Zhou, A. M. Rao, P. C. Eklund, M. S. Dresselhaus, and R. A. Jishi, Intramolecular Vibrational Mode Softening in Alkali-Metal Saturated  $C_{70}$  Films, Phys. Rev. (1993). accepted.
18. R. A. Jishi, L. Venkataraman, M. S. Dresselhaus, and G. Dresselhaus, Phonon Modes in Carbon Nanotubules, Chem. Phys. Lett. (1993). accepted, 4/21/93.